


**AMENDMENT TO THE CLAIMS:**


This listing of claims will replace all prior versions, and listings, of claims in the application:

**LISTING OF CLAIMS:**


1. (Currently Amended) A polyamic acid having repeating units represented by the formula (1):



wherein the norbornane skeleton of



comprises four components of



and their contents satisfy the following:

1 % ≤ 2,5-[diexo] ≤ 90 %,

1 % ≤ 2,5-[exo,endo] ≤ 90 %,

1 % ≤ 2,6-[diexo] ≤ 90 %,


$$1 \% \leq 2,6\text{-[exo,endo]} \leq 90 \%,$$

provided that


$$(2,5\text{-[diexo]}) + (2,5\text{-[exo,endo]}) + (2,6\text{-[diexo]}) + (2,6\text{-[exo,endo]}) = 100 \%,$$

R represents a tetravalent group having from 4 to 27 carbon atoms and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member, wherein the polyamic acid has an inherent viscosity measured in a solvent of N-methyl-2-pyrrolidone having an acid concentration of 0.5 g/dl at 35°C that falls between 0.1 and 3.0 dl/g.


2. (Original) A polyamic acid having repeating units represented by the formula (1):



wherein the norbornane skeleton of



comprises four components of



and their contents satisfy the following:

$$10 \% \leq 2,5\text{-[diexo]} \leq 40 \%,$$

$$10 \% \leq 2,5\text{-[exo,endo]} \leq 40 \%,$$

$$10 \% \leq 2,6\text{-[diexo]} \leq 40 \%,$$


$$10 \% \leq 2,6\text{-[exo,endo]} \leq 40 \%,$$

provided that


$$(2,5\text{-[diexo]}) + (2,5\text{-[exo,endo]}) + (2,6\text{-[diexo]}) + (2,6\text{-[exo,endo]}) = 100 \%,$$

R represents a tetravalent group having from 4 to 27 carbon atoms and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member.


3. (Original) A polyamic acid having repeating units represented by the formula (1):



wherein the norbornane skeleton of



comprises four components of



and their contents satisfy the following:

$$20 \% \leq 2,5\text{-[diexo]} \leq 30 \%,$$

$$20 \% \leq 2,5\text{-[exo,endo]} \leq 30 \%,$$

$$20 \% \leq 2,6\text{-[diexo]} \leq 30 \%,$$

$$20 \% \leq 2,6\text{-[exo,endo]} \leq 30 \%,$$


provided that

$$(2,5\text{-[diexo]}) + (2,5\text{-[exo,endo]}) + (2,6\text{-[diexo]}) + (2,6\text{-[exo,endo]}) = 100 \%,$$


R represents a tetravalent group having from 4 to 27 carbon atoms, and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed

polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member.


4. (Currently Amended) A polyimide having repeating units represented by the formula (2):



wherein the norbornane skeleton of



comprises four components of



and their contents satisfy the following:

$$1 \% \leq 2,5\text{-[diexo]} \leq 90 \%,$$

1 %  $\leq$  2,5-[exo,endo]  $\leq$  90 % ,

1 %  $\leq$  2,6-[diexo]  $\leq$  90 % ,


1 %  $\leq$  2,6-[exo,endo]  $\leq$  90 % ,

provided that


(2,5-[diexo]) + (2,5-[exo,endo]) + (2,6-[diexo]) + (2,6-[exo,endo]) = 100 % ,

R represents a tetravalent group having from 4 to 27 carbon atoms and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member, wherein the polyimide has an inherent viscosity measured in a mixed solvent of p-chlorophenyl/phenol = 9/1 (by weight) with a polyimide concentration of 0.5 g/dl at 35°C that falls between 0.1 and 3.0 dl/g.


5. (Original) A polyimide having repeating units represented by the formula (2):



wherein the norbornane skeleton of



comprises four components of



and their contents satisfy the following:

$$10 \% \leq 2,5\text{-[diexo]} \leq 40 \%,$$

$$10 \% \leq 2,5\text{-[exo,endo]} \leq 40 \%,$$

$$10 \% \leq 2,6\text{-[diexo]} \leq 40 \%,$$

$$10 \% \leq 2,6\text{-[exo,endo]} \leq 40 \%,$$


provided that

$$(2,5\text{-[diexo]}) + (2,5\text{-[exo,endo]}) + (2,6\text{-[diexo]}) +$$


$$(2,6\text{-[exo,endo]}) = 100 \%,$$

R represents a tetravalent group having from 4 to 27 carbon atoms and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member.


6. (Original) A polyimide having repeating units represented by the formula (2):



wherein the norbornane skeleton of



comprises four components of





and their contents satisfy the following:

$$20 \% \leq 2,5\text{-[diexo]} \leq 30 \%,$$

$$20 \% \leq 2,5\text{-[exo,endo]} \leq 30 \%,$$

$$20 \% \leq 2,6\text{-[diexo]} \leq 30 \%,$$

$$20 \% \leq 2,6\text{-[exo,endo]} \leq 30 \%,$$


provided that

$$(2,5\text{-[diexo]}) + (2,5\text{-[exo,endo]}) + (2,6\text{-[diexo]}) + \\ (2,6\text{-[exo,endo]}) = 100 \%,$$


R represents a tetravalent group having from 4 to 27 carbon atoms, and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member.

7. (Canceled)


8. (Original) A process for preparing a polyamic acid, which comprises reacting a mixture of diaminomethyl-bicyclo[2.2.1]heptanes, (2S,5S)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-1):




(2S,5R)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-2):



(2S,6R)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-3):



and (2S,6S)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-4):



wherein,

10 %  $\leq$  (2S,5S)-diaminomethyl-bicyclo[2.2.1]heptane  $\leq$  40 % ,


10 %  $\leq$  (2S,5R)-diaminomethyl-bicyclo[2.2.1]heptane  $\leq$  40 % ,

10 %  $\leq$  (2S,6R)-diaminomethyl-bicyclo[2.2.1]heptane  $\leq$  40 % ,

10 %  $\leq$  (2S,6S)-diaminomethyl-bicyclo[2.2.1]heptane  $\leq$  40 % ,


provided that,

(2S,5S) isomer + (2S,5R) isomer + (2S,6R) isomer + (2S,6S) isomer = 100 %,  
with a tetracarboxylic dianhydride represented by the formula (4):




wherein R represents a tetravalent group having from 4 to 27 carbon atoms and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member.


9. (Original) A process for preparing a polyamic acid, which comprises reacting a mixture of diaminomethyl-bicyclo[2.2.1]heptanes, (2S,5S)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-1):




(2S,5R)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-2):



(2S,6R)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-3):



and (2S,6S)-diaminomethyl-bicyclo[2.2.1]heptane of formula (3-4):



wherein,

20 % ≤ (2S,5S)-diaminomethyl-bicyclo[2.2.1]heptane ≤ 30 % ,

20 % ≤ (2S,5R)-diaminomethyl-bicyclo[2.2.1]heptane ≤ 30 % ,


20 % ≤ (2S,6R)-diaminomethyl-bicyclo[2.2.1]heptane ≤ 30 % ,

20 % ≤ (2S,6S)-diaminomethyl-bicyclo[2.2.1]heptane ≤ 30 % ,

provided that,

(2S,5S) isomer + (2S,5R) isomer + (2S,6R) isomer + (2S,6S) isomer = 100 % ,

with a tetracarboxylic dianhydride represented by the formula (4):



wherein R represents a tetravalent group having from 4 to 27 carbon atoms and selected from the group consisting of an aliphatic group, a monocyclic aliphatic group, a condensed polycyclic aliphatic group, a monocyclic aromatic group, a condensed polycyclic aromatic group, and a non-condensed polycyclic aliphatic or aromatic group which is composed of cycloaliphatic or aromatic groups mutually bonded to each other either directly or via a crosslinking member.

10. (Canceled)

11. (Original) A process for preparing a polyimide, which comprises thermally or chemically imidizing the polyamic acid obtained in claim 8.

12. (Original) A process for preparing a polyimide, which comprises thermally or chemically imidizing the polyamic acid obtained in claim 9.

13. (Previously Presented) The polyamic acid of claim 3, of which the inherent viscosity measured in a solvent of N-methyl-2-pyrrolidone having the acid concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

14. (Previously Presented) The polyimide of claim 6, of which the inherent viscosity measured in a mixed solvent of p-chlorophenyl/phenol = 9/1 (by weight) having the polyimide concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

15. (Original) A polyamic acid varnish containing the polyamic acid of claim 1.

16. (Original) A polyamic acid varnish containing the polyamic acid of claim 2.

17. (Original) A polyamic acid varnish containing the polyamic acid of claim 3.

18. (Original) A polyimide film containing the polyimide of claim 4.

19. (Original) An amorphous polyimide film containing the polyimide of claim 5.

20. (Original) An amorphous polyimide film of improved smoothness, containing the polyimide of claim 6.

21. (Previously Presented) The polyamic acid of claim 2, of which the inherent viscosity measured in a solvent of N-methyl-2-pyrrolidone having the acid concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

22. (Canceled)

23. (Previously Presented) The polyimide of claim 5, of which the inherent viscosity measured in a mixed solvent of p-chlorophenyl/phenol = 9/1 (by weight) having the polyimide concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

24. (Canceled)